# FASSON® 0821


Suitable for die-cut shapes, shielding, moisture and vapor barrier sealing components or lamination to insulation materials.

### **FEATURES:**

- High-strength reinforced 6.5 mil FSK facestock
- Quick stick, rubber-based adhesive
- Strong bleached 40# densified kraft liner

## **BENEFITS:**

- Strong bond to a variety of substrates
- Tri-directional FSK reinforces seal
- Product reliability
- Tested in accordance with UL 723
- Made in the USA



# CONSTRUCTION:

Carrier:

Scrim FSK Aluminum Foil

Adhesive:

Rubber

Liner:

Densified Kraft



General Use Tape Surface Burning Characteristcs to

UL 723 Flame Spread 10

Smoke Developed 15

**722S** 



# FASSON® 0821 Typical Values **Adhesive Properties:** IIS Mile MMI

Thickness	Test Method(s): PSTC-133	US Mils	MM's	Microns (μm)		
Liner:		3.2	0.08	81		
Adhesive:		2.0	0.05	51		
Carrier:		6.5	0.17	165		
Total Caliper:		11.7	0.30	297		
PEEL ADHESION	Test Method(s): PSTC-101, ASTI	M D-3330, STD-10				
Product 180º 12" min		11.671	110.0 //	N. ( P		
Substrate	1.78.1	Lbf / In	US Oz / In	N / Meter		
SS	Initial	6.5	104	1138		
-						
-						
LOOPTACK	Total Marks (V.) BOTO 40, 0770	7				
Droduct 1900 20" / min	Test Method(s): PSTC-16, STD-7	•				
Product 180° 20" / min		Lbf / In	US Oz / In	N / Meter		
Substrate	Initial	15.6	250	2732		
SS	IIIIIai	13.0	230	2132		
-						
-						
-						
+				+		
+				+		
+				+		
STATIC SHEAR	Test Method(s): PSTC-107, ASTI	M D 3654 STD-9				
Aluminum Foil 1/2" sq (3.25 c		VI D 000-1, 01D 0				
Substrate	1112) 2.2 lb (1.0 kg)	Min to Fail				
SS	Initial	> 10,000				
		,				
			1	-		
STATIC SHEAR	Test Method(s): PSTC-107, ASTI	M D 3654, STD-9				
Aluminum Foil 1" sq (6.5 cm <sup>2</sup>	1) 10 lb (4.5 kg)					
Substrate	,	%				
SS	@ 150°F / 65°C	> 10,000				
+						
			1	•		
TEMPERATURES		۰F		° C		
Min Application Temp		50 ° F		10 ° C		

THE	LISTED VALUES ARE TYPICAL AND N	OT	INTENDED TO	SERVE AS	S PRODUCT SPEC	CIFICATIONS

#### **APPLICATION TECHNIQUES**

Max Continuous Operating Temp

Max Intermittent Operating Temp

- It is essential, as with all pressure-sensitive tapes, that the surface to which the tape is applied be clean, dry, and free of grease or oil
- Bond strength is dependent upon the amount of adhesive-to-surface contact developed
- · Note that different pressure, time and temperature on different (film / rigid) surface achieves different performance

#### STORAGE / SHELF LIFE

• One year when stored at 64-72°F (18-22°C) / 30-70% relative humidity, out of direct sunlight and in original packaging.

Please refer to Tapes. Avery Dennison. com for complete terms and conditions, including warranty terms, relating to this product. You should periodically review the site as terms and conditions are subject to change without notice.

© 2015 Avery Dennison Corporation. All rights reserved. Avery Dennison® is a registered trademark of Avery Dennison Corporation. All other Avery Dennison brands, product names, antenna designs and codes or service programs are trademarks of Avery Dennison Corporation.



Asia Pacific Kunshan, China, NO. 618 Nanhe Road Kunshan Economic & Technological Zone China, 215335

Phone: +86 512 57155001 Fax: +86 512 57155059

Europe Tieblokkenlaan 1 B-2300 Turnhout Belgium

175°F

200 ° F

Phone: +32 (0)14 40 48 11 Fax: +32 (0)14 40 48 55

North America 250 Chester Street Painesville, Ohio 44077 USA

79°C

93 ° C

Phone: +1 866-462-8379 Fax: +1 888-358-4469